

MANNINGTON COMMERCIAL®

colorscape™/colorspec™ rubber tile stain resistant chart

chemical	colorscape™ colorspec™ rubber tile
acetic acid, 5%	1
acetone	1
acid, hydrochloric, 5%	0
alcohol, isopropyl, 70%	0
ammonia, 28%	0
ammonium hydroxide, 5%	0
animal blood	0
betadine	1
bleach, 5.25%	1
carbon tetrachloride	0
chloroform	0
cotton seed oil	0
disinfectant, 5% phenol	0
ethyl acetate	0
ethyl alcohol, 95%	0
formaldehyde, 37%	0
gasoline	1
hydrogen peroxide, 30%	0
methanol	0
mineral oil	0
muriatic acid, 0.5%	1
sodium hydroxide, 5%	0
sodium hydroxide, 50%	0
sulfuric acid, 98%	0
tallow	0
tincture of iodine, 2%	0
trichloroethylene	1
urine	0

solvent and stain resistance*

Notes: * Effect on surface attack, color change & surface dulling per ASTM F-925-96 (60 minute tests)

- 0: no change
- 1: slight change
- 2: moderate change
- 3: severe change