

DESCRIPTION

V-82 is a nonflammable, solvent-free, light-colored acrylic adhesive that provides good moisture and alkali resistance, and a strong bond for Mannington Commercial's homogeneous vinyl-backed products. Use over approved suspended wood floors and for on, above, or below-grade concrete. Refer to Mannington Professional Installation Guide

FEATURES

- Easy Application
- VOC-compliant / solvent-free / low odor
- Non-flammable
- Moisture- and alkali-resistant
- Readily identifiable mylar chips
- Contains fungicide protection
- Complies with SCAQMD Rule 1168

DIRECTIONS

- Make sure the underfloor is clean and free of all foreign matter such as dirt, paint, oil, wax, etc. It should be smooth and level. Sand off high spots and fill low spots, cracks, holes, etc., with the appropriate patching compound.
- The building must have permanent heat / air.
- Maintain the adhesive, floor covering, and jobsite at a temperature of at least 65°F for a minimum of 48 hours before, during, and after installation.
- V-82 adhesive should be applied with a trowel having notches 1/16" wide, 1/32" deep, spaced 1/32" apart.
- The adhesive must be spread over 100% of the exposed subfloor, leaving no gaps or puddles. Uniform coverage can be maintained by keeping the trowel clean and properly notched.
- Provide adhesive open time but do not allow the adhesive to "skin over" before laying the floor covering into the adhesive. V-82 has a 30-minute working time after spread.
- After the adhesive has been applied, roll the sheet forward into the adhesive to eliminate trapping air. Do not drop or flop the material into the adhesive. Roll the floor covering with a three-section, 150-lb floor roller in both directions.
- Fresh adhesive smears can be cleaned with water. Remove dried adhesive with mineral spirits or painter's naphtha.
CAUTION: Mineral spirits and naphtha are flammable.
- Avoid heavy traffic on the finished floor for at least 24 hours.
CAUTION: All non-porous substrates must be rendered porous by applying an appropriate overlay of a cementitious product before applying V-82.

COVERAGE

Approximately 150-200 sq ft per gallon.

PACKAGING

4-Gallon Pail #849882, weighs 46.4 lbs (21.05 kg)

PRECAUTIONS

- Use with adequate ventilation.
- Do not use where **excessive** moisture, alkali, or hydrostatic pressure exists.
- Prevent prolonged breathing of vapor and skin contact.
- Do not ingest.
- Avoid contact with eyes.
- **KEEP OUT OF THE REACH OF CHILDREN.**